

		DBX	DBA
		Solvent Base	Solvent Base
Air Cure	Surface Dry	1 - 2 hours @ 25 °C	8 hours @ 25 °C
	Air Dry	3 - 5 days @ 25 °C	3 - 5 days @ 25 °C
Thermal Cure (Oven)		30 minutes @ 130 °C	30 minutes @ 130 °C
		10 minutes @ 200 °C	10 minutes @ 200 °C
Application	Wiping	x	✓
	Brushing	✓	✓
	Dipping	✓ Clean Room Required	✓ Clean Room Required
	Spraying	✓ Clean Room Required	✓ Clean Room Required
Pencil Hardness		Up to 9H	Up to 9H
Thickness of Coating		Up to 30 micron	Up to 20 micron
Viscosity (#2 Zahn Cup)		14 seconds	10 seconds
Substrate		Metal, Stone, Wood	Metal, Stone, Wood, Non-Absorbent Leather
Standard Consumption (Non-porous surface)		900 cm ² /ml	900 cm ² /ml